



Plastic & polymer additives and solution supplier
E:info@novistagroup.com I : www.novistagroup.com

Technical Data Sheet

ProFlame® - FR Masterbatch

EFPO-240170M

Environment-friendly PP Flame Retardant Masterbatch for UL94-V0 Class. Developing its effectiveness through phosphorus/nitrogen synergism. When the polyolefin on exposure to flame, the carbon foam layer formed protects the polymer through its heat insulating effect to reduce further oxygen access and prevent dripping of the polymer.

Tech Spec:

Item	Index
Appearance	White Granule
Moisture	0.3% max
Density	1.2±0.1 g/cm ³
Decomposition Temperature	240°C min
FR Grade(UL94)	V0 (1.6-3.2mm)

Applications:

The extrusion and injection of PP,PE and other polyolefins for V0 grade under UL94.

Recommended dosage :

Polymer	Usage guide
PP	UL94 V0-3.2mm : 34-36 wt% UL94 V0-1.6mm : 38-40 wt%
PE	UL94 V0-3.2mm : 39-41wt% UL94 V0-1.6mm : 45-50wt%

Processing instruction:

- ▶ The optimum conditions for incorporating should be determined in each individual case. Care must be taken to ensure homogeneous dispersion of all components.
- ▶ Both single- and twin-screw extruders are suitable for incorporating the product. The temperature of the polymer melt should not exceed 240°C.

Package & Storage:

Net weight 25KG bag with PE liner.

It is not dangerous cargo .You should handle the material according to the instruction described on MSDS.

+86-536-8206760

info@novistagroup.com

www.novistagroup.com

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Novista Group and its subsidiaries. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.